



Samarium Cobalt / Magnetic Properties

Grade	Press ¹	Type ²	Br (Gauss)	Hc (Oersteds)	Hci (Oersteds)	BHmax (MGOe)	Temperature Coefficients (%°C)		Maximum Operating Temp @ Pc = 2 ³	
			Range	Typical	Minimum	Range	of Br	of Hci	(°C)	(°F)
S3007	D	2:17	10,500 ~ 11,200	8,250	7,000	24 ~ 30	-0.04	-0.17	~ 250	~ 480

¹ D: Die-Pressed, I: Isostatically-Pressed

² Type: Sm₁Co₅ or Sm₂Co₁₇ types

³ The Maximum Operating Temperature shown here is for magnets operating at a Permeance Coefficient of 2. At the temperatures shown the operating point of the material is above the knee of the BH Curve.

Samarium Cobalt / Physical Properties

Grade	Density		Bending Strength		Compressive Strength		Electrical Resistivity (Ωm)	Coeff. of Thermal Expansion ⁴		Curie Temperature	
	(kg/m ³)	(lbs/in ³)	(kg/m ²)	(lbs/in ²)	(kg/m ²)	(lbs/in ²)		// M	⊥M	(°C)	(°F)
S3007	8.4 x 10 ³	0.304	1.2 x 10 ³	1.7 x 10 ⁴	9.1 x 10 ³	1.3 x 10 ⁵	0.8 x 10 ⁻⁶	9.7 x 10 ⁻⁶	12.2 x 10 ⁻⁶	825	1510

⁴// M Parallel to magnetic orientation, ⊥M Perpendicular to magnetic orientation.